

STA²-PUT[®]

SPHS

Canister Contact Adhesive

SPHS is a non-flammable aerosolized contact adhesive with pressure sensitive properties. Its superior bond strength and exceptional tack make it an excellent choice for most permanent adhesive applications. *SPHS*'s convenient canister and user-friendly spray pattern make it an ideal adhesive for high speed production. *SPHS* contains zero VOCs and utilizes a patented propellant system for non flammability.

FEATURES

- ◆ Non-Flammable
- ◆ Aggressive Grab Tack
- ◆ High Green Strength
- ◆ Excellent adhesion to many substrates
- ◆ Patented propellant system, Patent # 7,708,980
- ◆ High Strength Bonds
- ◆ Self-contained portable spray system
- ◆ Flatwork applications (non-postforming)
- ◆ Long Open Time

SUSTAINABILITY GUIDE

GREENGUARD[®] Children & Schools Certified

GREENGUARD[®] Indoor Air Quality Certified

- **CHPS[®] (Collaborative for High Performance Schools) EQ Credit 2.2**



DIRECTIONS:

Use only after careful consideration of the warnings, directions, and first aid instructions given. Do not thin. Surfaces to be bonded should be clean, dry and free of any dust, loose paint, wax, moisture, dirt, grease, oil, rust, or other contaminants. Before initial use securely attach gun to hose, then hose to canister. Fully open canister valve; do NOT close valve until empty. Adhesive should be at 60°F to 95°F. For best results, adhesive and materials to be bonded should be 60°F (15.6°C) to 95°F (35°C) during application. Allow substrates to acclimate to room temperature for 48 hours before bonding. Spraying from 8 to 12 inches away, apply adhesive uniformly to both surfaces and cover each surface a minimum of 80%. Some porous surfaces may require two coats. 100% coverage is recommended for the edges. Use only approved equipment. For typical applications a coating weight of 2.5 dry grams per square foot is recommended. Both surfaces must be allowed to dry before bonding. This will usually take from 2 to 5 minutes at room temperature under normal conditions. Heat and humidity, or cold weather can effect drying times. Surfaces are dry if adhesive is tacky, but no adhesive transfers to the hand when touched. Complete the bond within 60 minutes (under normal conditions) after the adhesive is dry. If the two surfaces don't grab immediately when brought into contact, they have dried too long. Position coated surfaces carefully before putting them together since no shifting is possible once contact is made. Bring surfaces together and immediately apply firm pressure over entire surface working from the center to the edges. Apply a minimum of 30 psi uniform pressure over 100% of the area being bonded. Let bonded parts cure for at least 72 hours before exposing to direct sunlight of temperatures over 150° F (65.6°C). Do not use on some vinyls or polystyrene foam. Some vinyls contain plasticizers, which can, over time, soften and dissolve the bond, or bleed through/discolor. When in doubt, or if product is to be used on vinyls, or other light colored materials, conduct compatibility testing on the product to be bonded before use. After initial assembly, leave the hose and gun attached to the canister with the valve open. After safely releasing line pressure, detach gun and hose only when transferring to a new canister. Reattach gun and hose immediately.

ITW TACC

56 Air Station Industrial Park

Rockland, MA 02370

Phone 1-800-503-6991 Fax 1-800-231-8222

info@itwtacc.com www.itwtacc.com

SPHS

Canister Contact Adhesive

NOTE: The shelf life for an unopened container of this adhesive stored at temperatures between 60°F (15.6°C) and 95°F (35°C) is 1 year from date of manufacture. Store out of direct sunlight in a cool, well-ventilated area. Avoid storing container directly on the floor or against an outside wall.

ATTENTION: Empty container remains hazardous until all vapors are gone from residue and container. Observe all labeled hazard precautions. Do not cut, puncture, or weld while hazard exists. Do not reuse empty container. Recycle, or dispose of, according to all federal, state, and local regulations.

NOTICE: Reports have associated repeated and prolonged occupational exposure to solvents with permanent brain and nervous system damage.

PHYSICAL PROPERTIES

BASE:	Synthetic Polymer	WEIGHT/GALLON:	10.20 lbs/gallon
SOLVENT:	Methylene Chloride	VOC CONTENT:	0 g/L (EPA Method 24)
SHELF LIFE:	1 year from date of manufacture	VISCOSITY:	90-140 cps
COLORS:	Clear /Red	OPEN TIME:	60 minutes
FLASHPOINT:	N/A	DRY TIME:	2-5 minutes

FORMALDEHYDE: No urea formaldehyde added during adhesive manufacturing

APPROVED EQUIPMENT

Spray Gun:	SG200
Spray Tip:	ST6502
Hoses:	MH973 (12'), MH974, (18'), MH978 (25')
T-Bar:	MH976

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL OR INDUSTRIAL USE ONLY
USE ONLY WITH APPROVED EQUIPMENT
SALE TO CONSUMER IS IN VIOLATION OF FEDERAL LAW**

NOTICE TO PURCHASER: NO WARRANTIES, EXPRESS OR IMPLIED, ARE MADE INCLUDING MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE. EXCEPT FOR PERSONAL INJURY RESULTING FROM USE OF THE PRODUCT AS DIRECTED, ITW TACC SHALL NOT BE LIABLE IN TORT OR CONTRACT FOR ANY LOSS OR DAMAGE. UNDER NO CIRCUMSTANCES SHALL ITW TACC, A DIVISION OF ILLINOIS TOOL WORKS INC., OR ITS AFFILIATES ("ITW TACC") BE LIABLE FOR ANY LOSS OR DAMAGE ARISING FROM THE PURCHASE, USE, OR INABILITY TO USE THIS PRODUCT, OR FOR ANY SPECIAL, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES. THE USER MAY SEND A SAMPLE OF PRODUCT TO ITW TACC FOR TESTING. IF SUCH TESTING PROVES A PRODUCT DEFECTIVE, THE USER'S SOLE AND EXCLUSIVE REMEDY IS EITHER REIMBURSEMENT OF THE PURCHASE PRICE OF THE PRODUCT OR REPLACEMENT OF THE CONTAINER OF PRODUCT. NO FABRICATOR, INSTALLER, DEALER, AGENT OR EMPLOYEE OF ITW TACC HAS THE AUTHORITY TO MODIFY THE OBLIGATIONS OR LIMITATIONS OF THIS WARRANTY. This warranty gives you specific legal rights, and you may also have other rights, which vary from state to state; therefore, some of the limitations stated above may not apply to you. It is to your benefit to save your documentation upon purchase of a product. The information and suggestions for use contained herein are believed to be accurate, but are not to be construed as warranties. User shall determine the suitability of the product for his or her intended use and shall assume all risk associated therewith.

Please direct all inquiries regarding performance of this product to:
ITW TACC, 56 Air Station Industrial Park, Rockland, MA 02370
Phone 1-800-503-6991 Fax 1-800-231-8222

info@itwtacc.com

www.itwtacc.com

Rev 7/10

