



GUN ' N GO

Gun 'N Go is a multi-purpose, non-flammable, PVA based, mastic-type adhesive especially formulated for fabricating wall systems for the manufactured housing industry.

FEATURES

- ◆ Non Flammable
- ◆ Bonds many common construction materials
- ◆ PFS[®] Certified (Listed # 15090901) to meet ASTM-C557 specifications
- ◆ U.S. Patent Nos. 6,381,918 B1 and 6,381,918 B2
- ◆ Easy to apply
- ◆ Meets ASTM E72

REGULATORY COMPLIANCE

- SCAQMD (South Coast Air Quality Management District), Rule 1168
- California Air District Regulations
- Ozone Transport Commission (OTC) model Rule for Adhesives and Sealants

DIRECTIONS

Apply adhesive just prior to panel assembly. Place in standard cartridge gun. Double Cut tip (following an "X" pattern) to create a 3/8" bead, do not "smear" bead. Puncture seal inside of spout with nail or wire. Place panels within 5 minutes of extruding adhesive (or while adhesive is still wet to touch). Drop panel into position, avoid sliding panel. Staple panel perimeter (including headers) 6" on center.

Tools and excess materials should be cleaned with water while Gun 'N Go is in the wet state. Use Mineral spirits to clean when dry.

In wiping adhesive smears off work, avoid flooding the area to be cleaned since excess solvent can work into seams, softening the bond line and causing delamination. Use a cloth that is saturated with solvent but not dripping. Keep solvent contact at the edges and seams of the lamination to a minimum to avoid the danger of softening the bond line. The sooner the smears are removed the easier it is to remove them.

Apply at room temperature. Do not thin.

ITW TACC

56 Air Station Industrial Park
Rockland, MA 02370

Phone 1-800-503-6991 Fax 1-800-231-8222
info@itwtacc.com www.itwtacc.com

GUN ' N GO

PHYSICAL PROPERTIES

BASE:	Synthetic Polymer	WEIGHT/GALLON:	11.17 lbs/gallon
SOLVENT:	Water	VOC CONTENT:	44.7 g/L (EPA Method 24)
COLORS:	Tan	VISCOSITY:	250,000-287,500 cps
SOLIDS:	75.1%	OPEN TIME:	5-10 minutes
FLASHPOINT:	N/A	COVERAGE	38 linear feet using 3/8" bead 86 linear feet using 1/4" bead



FREEZE/THAW: DO NOT FREEZE

SHELF LIFE: 6 months from date of manufacture

FORMALDEHYDE: No urea formaldehyde added during adhesive manufacturing

**KEEP OUT OF REACH OF CHILDREN
FOR PROFESSIONAL OR INDUSTRIAL USE ONLY**

NOTICE TO PURCHASER: NO WARRANTIES, EXPRESS OR IMPLIED, ARE MADE INCLUDING MERCHANTABILITY AND/OR FITNESS FOR A PARTICULAR PURPOSE. EXCEPT FOR PERSONAL INJURY RESULTING FROM USE OF THE PRODUCT AS DIRECTED, ITW TACC SHALL NOT BE LIABLE IN TORT OR CONTRACT FOR ANY LOSS OR DAMAGE. UNDER NO CIRCUMSTANCES SHALL ITW TACC, A DIVISION OF ILLINOIS TOOL WORKS INC., OR ITS AFFILIATES ("ITW TACC") BE LIABLE FOR ANY LOSS OR DAMAGE ARISING FROM THE PURCHASE, USE, OR INABILITY TO USE THIS PRODUCT, OR FOR ANY SPECIAL, INDIRECT, INCIDENTAL, OR CONSEQUENTIAL DAMAGES. THE USER MAY SEND A SAMPLE OF PRODUCT TO ITW TACC FOR TESTING. IF SUCH TESTING PROVES A PRODUCT DEFECTIVE, THE USER'S SOLE AND EXCLUSIVE REMEDY IS EITHER REIMBURSEMENT OF THE PURCHASE PRICE OF THE PRODUCT OR REPLACEMENT OF THE CONTAINER OF PRODUCT. NO FABRICATOR, INSTALLER, DEALER, AGENT OR EMPLOYEE OF ITW TACC HAS THE AUTHORITY TO MODIFY THE OBLIGATIONS OR LIMITATIONS OF THIS WARRANTY. This warranty gives you specific legal rights, and you may also have other rights, which vary from state to state; therefore, some of the limitations stated above may not apply to you. It is to your benefit to save your documentation upon purchase of a product. The information and suggestions for use contained herein are believed to be accurate, but are not to be construed as warranties. User shall determine the suitability of the product for his or her intended use and shall assume all risk associated therewith.

Please direct all inquiries regarding performance of this product to:
ITW TACC, 56 Air Station Industrial Park, Rockland, MA 02370
Phone 1-800-503-6991 Fax 1-800-231-8222
info@itwtacc.com www.itwtacc.com

12/11